



INSTALLER GUIDE

WINDOW +

Artदेशine Pte. Ltd.
Company Reg. No. 201915850R

Address:
101 Woodlands Ave 12, #04-30/31,
Singapore 737719

Email: hello@artदेशine.co

Printed in Singapore
WWW.ARTDESHINE.CO

Surface suitability: Formulated specially for glass windows/windshield. Can also be used on gloss/matte clear coats on automotive body or wheel, vinyl wraps, paint protection film (PPF) wraps, acrylic parts, gloss/matte plastic trims and fittings

(installing on other areas of automotive may affect durability)
(windshield compatibility may vary with age, make, model of vehicle and wiper type, use this product at your own risk, wiper movement issues may occur)

Chemical resistance: pH3 – pH13

Thermal threshold on treated surface (onset of degradation): 300°C

Liquid substance repellence of treated surface:

- Distilled water droplet average contact angle –110-120°
- Vegetable oil droplet average contact angle –80-90°

Average Water Sliding Angle on coated clear coat surface: 24.4°

Hologram (swirls) reduction during application:

- Micro-mesh >9000
- FEPA sandpaper grade >P7000

Consumption rate: 2-3 ml/m²

Curing time (recommended):

2 hours (tropical/humid) / 12 hours (temperate/dry) or 0.5 hour Infrared assisted

- Surface dry (unaffected contact with water/rain)

4 days (tropical/humid) / 7 days (temperate/dry) with or without infrared assisted curing

- Unaffected contact with cleaning solutions
- Unaffected contact with contaminants (tree-sap/bird droppings etc.)
- Exposure to harsh environmental conditions

(Exposure before curing may result in diminished bonding, early deterioration of coating, occurrences of water-spotting, etching or corrosion)

Appearance after curing: Optically transparent, visibly increased reflectivity

Solvent incompatibility:

N-Methylpyrrolidone (NMP), Tetrahydrofuran (THF), Chloroform, Ether.
(the use of products containing these solvents during application causes swelling/gelation)



Window +

Technical Specifications

Contains ingredients (General terms): polydimethylsiloxane, bis[3-(triethoxysilyl)propyl]amine, naphtha petroleum, isopropanol, carbon nanotubes, sodium dodecylbenzenesulfonate

Solubility with water (in bottle): Not miscible

Appearance and odour (in bottle): Black viscous solution, non-pungent odour

Capabilities listed are maximum approximates and based on a single coat application on automotive glass window and windshield that has been cleaned, decontaminated, polished with fine sandpaper and appropriately prepared. More information for preferred after-care to maximise durability available.

Bonding durability (normal conditions): 2 Years

- 100 washes pH neutral
- Climate range -20°C to + 35°C

Bonding durability (extreme conditions): 2 Years

- 50 washes pH 4>12
- Climate range -40°C to + 40°C

Hydrophobic properties durability (normal conditions): 2 Years

- 100 washes pH neutral
- 50 washes pH 4>12

Durability will be reduced if wiper is frequently used as the blades will erode the coating.

Average coating thickness (2-3 ml/m² with 10 minutes dwell time): 2.0 – 3.0 µm (micrometre/micron)

Hardness (SHORE A Scale): 43

Dirt Pickup Resistance (ASTM-D3719): 59.8ΔL

Products containing solvents such as acetone, 1-propanol, methanol, water, 2-propanol (IPA) in small amounts can be used with no significant impact. (Contact Artदेशine to find out about product compatibility.)

Application

Before application of product, ensure surface is stripped of all existing products (waxes, sealants and spray detailers etc.).

Working area should

- Minimise levels of dust, moisture, heat and environment contaminants for maximum bonding effectiveness.
- Have sufficient lighting for better visibility of both top facing surfaces and side facing surfaces. Combination of warm (<3000K) and cool lighting (>4000K) will help with a proper installation.
- Have appropriate ventilation systems to avoid inhaling of vapours/gas
- No open flames, lighted cigarettes, running ovens or heating devices blow torches, heat guns etc.)

Do not apply product under direct sunlight or a heated surface.

- Optimal surface temperature < 25°C
- Optimal ambient temperatures < 32°C

If natural sedimentation occurs, shake the bottle well to evenly disperse the product and wait 1 minute before unscrewing cap slowly to release gas build-up

1. Make all necessary preparation like compounding, polishing, claying, decontamination, washing and cleaning before application process.
2. Utilise panel wipes, isopropyl alcohol (IPA), silicone removers to remove oil, fillers and polishing compounds. (e.g. Artदेशine Prep)
3. Drip 3ml (6ml if priming applicator) drops of product by dragging tip of bottle in a straight line to and fro on any suede, microfiber applicator block or pads.
4. Apply onto surface no larger than 1.0m x 1.0m in circular motion and cross-hatch motion for even coverage.
5. Applied product should look like spreading liquid glue, not dripping wet.
6. Product will turn slightly cloudy after 15-20 seconds, wait at least 5 minutes up to a maximum of 15 minutes or less depending on ambient temperatures.
7. Starting from the edges of applied area, wipe off excess with a clean and dry microfiber (MF) towel. (grabby feeling MF towel is normal for this step)

8. Using another clean and dry MF towel, buff off all residue, hazing, high-spots and smears in circular motion.
9. Check for any remaining high-spots, smearing, uneven colour tones and streaking.
10. Ensure surface is clear and surface feels slick. (smoothness can be felt when buffing with MF towel)
11. Repeat step all steps for adjacent areas. Take extra care at edges where applied and un-applied surfaces meet. Always apply and buff over the edges to ensure smooth joining.

Multiple coats is not necessary and can be a wastage of product. A maximum of 2 coats will be more than sufficient and to cover any missed out areas and enhance coating mechanical strength.

To apply multiple coats, allow 2 hours (tropical/humid) or 12 hours (temperate/dry) in between coats.

Do not apply other coating, sealant, wax and spray detailer products immediately before and after application as this will affect the performance and bonding.

Any issues should be resolved using above methods in the first 15 minutes after application as the coating will not have started curing.

Last resort removal 1 hour after application can be done with Artdeshine Prep or any panel wipes and IPA.

After 24 hours, any issues will have to be resolved by removal of the coating and re-applying. This can be done with a polishing machine using fine pads and compounds.

Recommended After-Care (Before Full Curing)

Before 0.5 hour (infrared assisted) or 2 hours:

- Do not allow surface to be exposed to rain or water.
- Do not allow surface to come into contact with harsh substances (bird droppings, plant sap, bug splatter, cleaners, shampoos etc.).
- If contact occurs, gently clean with damp MF towel or soft napkin using fresh water. Wipe dry with another dry MF towel or soft napkin.

Before 7 days with or without infrared assisted curing:

- Do not allow surface to come into contact with harsh substances (bird droppings, plant sap, bug splatter, cleaners, shampoos etc.).

- If contact occurs, wipe gently with damp MF towel or soft napkin using fresh water.
- If substance has dried, place slightly wet MF towel or wet napkin to soften before wiping off gently.
- Exposure to rainwater will not affect curing process.
- However, ensure that rainwater is not on the surface for prolonged periods by drying with MF towel when weather permits.
- Any harsh substances or rainwater on surface exposed to sunlight and heat may cause stains, marks and spotting on uncured coating.
- Cleaning can be done with a damp MF towel using fresh water. Wipe and dry gently.
- Cleaning can also be done with Artdeshine GrapheneSeal and Bio Nano in higher dilution (1:19) with fresh water.

Recommended After-Care (After Full Curing)

Every 1-2 weeks:

- Washing should be done with pH neutral or paint compatible shampoo. (e.g. Artdeshine AlkClean or CitrusClean)

Every 1-2 months (user preference):

- Washing can be done with Alkali shampoo (e.g. Artdeshine AlkClean) no more than pH 12 for deeper cleansing and removal of oils/traffic film. Oil trapped in the pores or on the surface will affect the water repellence performance.

Every 2-4 months:

- Application of ceramic spray sealants. (e.g. Artdeshine Bio Nano or GrapheneSeal)

Every 4-6 months:

- Removal of embedded contaminants using fine grade clay bars or cloth. This is important in keeping the surface smooth and slick. A rough surface will affect the water repellence performance.
- Application of ceramic spray sealants. (e.g. Artdeshine Bio Nano or GrapheneSeal) for slickness, gloss and water repellent properties.
- Application of Artdeshine BX+ Coating for better water repellent effect and self-cleaning properties.

Do not apply any other coating, wax or sealant products as additional or top coats unless recommended by Artdeshine as it may affect or alter the coating's performance. Water soluble products like spray sealants are milder and more suitable. More information on product compatibility or other Artdeshine products for after-care is available through your distributors or contact Artdeshine directly for more information

4

5

Storage and Warning

This serves as basic and commonly needed information for safe handling and use of products. Material Safety Data Sheet available upon request for more specific information.

Shelf-life:

- 2 years unopened
- 6 months after unscrewing cap

Storage environment:

- < 30°C ambient temperature or gelation may occur.
- Keep containers securely sealed.
- Store in a cool, dry, well-ventilated area.
- Segregate from alcohol, water.
- No smoking, naked lights, heat or ignition sources.
- Do NOT store near acids, or oxidising agents.

Sedimentation:

- May occur if stored still for more than 1 month
- Shake well until product is evenly dispersed or before use
- Always uncup carefully to release gas build-up after shaking bottle

DANGER.

Hazard Statements:

H302: Harmful if swallowed.

H304: May be fatal if swallowed and enters airways.

H336: May cause drowsiness or dizziness.

H314: Causes severe skin burns and eye damage.

Precautionary Statements

P260: Do not breathe mist/vapours/spray.

P264: Wash all exposed external body areas after handling.

P271: Use only outdoors or in well-ventilated areas.

P301+P310+P330+P331: IF SWALLOWED: Immediately call a POISON CENTER/ doctor/first-aid. Rinse mouth, do NOT induce vomiting. If more than 15 mins from Doctor, INDUCE VOMITING (if conscious)

P303+P361+P353: IF ON SKIN (or hair): Remove contaminated clothing. Rinse skin with water.

P405: Store locked up.

P403+P233: Store in a well-ventilated place. Keep containers tightly closed.

P501: Dispose of containers/content to authorised hazardous or special waste collection points in accordance with local regulations.



Scan QR to watch application.



This installer guide might have been updated since printing, visit <https://artdesline.co/support/> for the latest installer guides and instructions.

6

7